

## SPECIFICATIONS

Commercial AMS-T-9046

Titanium Alloy Ti-3Al-8V-4Mo-4Zr / UNS R58640 in sheet, strip and plate is used for high strength structural applications.

## CHEMICAL COMPOSITION

AMS T 9046 Titanium Alloy	
Element	% Present
Vanadium (V)	7.5 - 8.5
Chromium (Cr)	5.5 - 6.5
Molybdenum (Mo)	3.5 - 4.5
Zirconium (Zr)	3.5 - 4.5
Aluminium (Al)	3 - 4
Others (Total)	0.4 max
Iron (Fe)	0.3 max
Oxygen (O)	0.12 max
Other (Each)	0.1 max
Carbon (C)	0.05 max
Nitrogen (N)	0.03 max
Hydrogen (H)	0.02 max
Yttrium (Y)	0.01 max
Titanium (Ti)	Balance

## ALLOY DESIGNATIONS

Titanium B-3 / Ti-3Al-8V-4Mo-4Zr / UNS R58640 is similar to the following specifications **but may not be a direct equivalent:**

SAE AMS 4900  
SAE AMS 4901  
SAE AMS 4902  
SAE AMS 4907  
SAE AMS 4909  
SAE AMS 4910  
SAE AMS 4911  
SAE AMS 4911G  
SAE AMS 4915  
SAE AMS 4916  
SAE AMS 4917  
SAE AMS 4918  
SAE AMS 4919  
SAE AMS T 9046  
SAE MAM 4911

## SUPPLIED FORMS

- Plate
- Sheet
- Strip

## MECHANICAL PROPERTIES

AMS T 9046 Titanium Alloy	
Property	Value
Proof Stress	827 Max MPa
Tensile Strength	862 Min MPa
Elongation A50 mm	6 Min %

The Mechanical Properties shown are for the ST Conditions.

For the STA condition Minimum Proof 1172 is MPa and Minimum Tensile is 1241 MPa

## CONTACT

Address:	Gould Alloys Ltd Markham Lane Markham Vale Chesterfield S44 5HS United Kingdom
Tel:	+44 (0) 1246 263300
Email:	sales@gouldalloys.co.uk
Web:	www.gouldalloys.co.uk

## REVISION HISTORY

Datasheet Updated	19 February 2015
-------------------	------------------

## DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.